



## **Sanitary Sealing Strip**

Revision: 25/11/2021 Page 1 from 2

#### **Technical data**

Carrier	TPE
Adhesive layer	Butyl Rubber
Release liner	Siliconized foil
Thickness (carrier + adhesive)	1,70 mm
Application temperature	5 °C → 30 °C

<sup>\*</sup> These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.

## **Product description**

Sanitary Sealing Strip is a self-adhesive sealing tape for waterproof sealing joints along bath, shower tray, wash-basin, countertop, sink, floor and tiles. Quick and easy to apply alternative to traditional sealants.

## **Properties**

- Watertight
- Easy to apply
- Very good adhesion on almost all substrates.
- Tear resistant
- Colourfast
- No drying time, continue working immediately
- Solvent free

## **Applications**

- Waterproof sealing of joints along bath, shower tray, wash-basin, countertop, sink, floor and tiles.
- As an alternative to traditional sealants.
- Only for interior use

## **Packaging**

Colour: white Packaging: roll Length (m): 3,35 Thickness (mm): 1,7 Width (mm): 22, 38

#### Shelf life

At least 24 months in original, unopened packaging at a cool and dry storage place, between +5°C and +40°C. Storage above +50°C may lead to difficulties in removing the release liner.

#### **Substrates**

Substrates: The most common substrates in bathrooms and kitchens: bath, shower tray, wash-basin, sink, floor and tiles. Not suitable for PE, PP, PTFE and bitumen

*Nature*: rigid, clean, dry, free of dust and grease. Ensure that frost or condensation are absent on the surface.

Surface preparation: Carefully degrease the surface with Soudal Surface Cleaner or acetone (the latter is not suitable for plastics). A preliminary adhesion test on every surface is recommended.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





# Sanitary Sealing Strip

Revision: 25/11/2021 Page 2 from 2

## **Application method**

Application method: Cut the Sanitary Sealing Strip to size and take 1 cm extra as a margin. If the strip is a bit stiff, it can be softened by gently warming it up on the radiator or using a hair dryer.

Fold the strip in half over its entire length and remove a small section of the release liner. Apply the strip to the corner of the longest joint and press firmly.

Remove the remaining release liner and continue to press firmly and evenly without stretching the strip. Cut off the excess strip at the end of the joint.

Adhere the strips in the corners over one another, then cut the overlapping parts in a 45° angle, remove the loose pieces and press the corner firmly again.

To obtain a better adhesion you can heat the strip with a hairdryer for 10 sec. immediately after application.

Check if the Sanitary Sealing Strip adheres well everywhere (especially in tile joints) and wait 24 hours before using the sanitary ware.

Cleaning: Adhesive residues can be removed with Soudal Adhesive Remover-CT or Soudal Surface Cleaner.

Repair: With the same material.

## **Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

## Remarks

- Not suitable for expansion and dilatation joints.
- The applied pressure and not the duration of the compression will determine the ultimate strength of the bond.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 B-2300 Turnhout, Belgium

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com